

RECEIVED
APR 29 2003
GROUP 1700

EXPRESS MAIL CERTIFICATE

4/24/03 294039989-US

Date

Label No.

I hereby certify that, on the date indicated above, this paper or fee was deposited with the U.S. Postal Service & that it was addressed for delivery to the Assistant Commissioner for Patents, Washington, DC 20231, by "Express Mail Post Office to Addressee" service.

Name (Print)

Signature

PLEASE CHARGE ANY DEFICIENCY UP TO \$1,000.00 OR CREDIT ANY EXCESS IN THE FEES DUE WITH THIS DOCUMENT TO OUR DEPOSIT ACCOUNT NO. 04 - 0100

Customer No.:



07278

PATENT TRADEMARK OFFICE



Docket No: 9626/1L207-US1

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re Application of: Tetsuya ATSUMI et al.

Serial No.: 09/473,495

Art Unit: 1733

Confirmation No.: 1052

Filed: December 28, 1999

Examiner: J. R. Fischer

For: SHAFT FOR LIGHT-WEIGHT GOLF CLUBS

PENDING CLAIM AS OF APRIL 24, 2003

20. A method for forming a golf club shaft around a mandrel having a length along a longitudinal axis, the steps comprising:

forming a first reinforcement layer from a first fiber material, said first fiber material having fibers aligned along a single direction;

forming a first angled layer by bonding second and third fiber materials, such that the fibers of said second material form a first angle with the fibers of said third material, said second and third materials having fibers aligned along a single direction;

forming a first straight layer from a fourth fiber material, said fourth fiber material having fibers aligned along a single direction;

forming a second angled layer from fifth and sixth fiber material, said fifth and sixth materials having fibers aligned along a single direction;

bonding said fifth and sixth fiber materials together to form said second angled layer, such that said fibers of said fifth and sixth material form a second angle in the range of from 70-150 degrees and said second angled layer has a thickness in the range of from 0.04 to 0.1 mm;

forming a second straight layer from a seventh fiber material, said seventh fiber material having fibers aligned along a single direction;

forming a second reinforcement layer from an eighth fiber material, said fiber material having fibers aligned along a single direction;

wrapping said first reinforcement layer around said mandrel such that said fibers of said first reinforcement layer are aligned 90 degrees with respect to said longitudinal axis;

wrapping said first angled layer around said first reinforcement layer such that said first angle of said fiber material of said first angled layer is bisected by said longitudinal axis;

wrapping said first straight layer around said first angled layer such that said fibers of said first straight layer are aligned with said longitudinal axis;

wrapping said second angled layer around said first straight layer such that said second angle of said fiber material of said second angled layer is bisected by said longitudinal axis;

wrapping said second straight layer around said second angled layer such that said fibers of said second straight layer are aligned with said longitudinal axis;

wrapping second reinforcement layer around said second straight layer to form a layered wrap, such that said fibers of said second reinforcement layer are aligned with said longitudinal axis;

curing said layered wrap in an oven to form a cured shaft;

removing said mandrel from said cured shaft; and

trimming ends said cured shaft to produce said golf club shaft.